

**SECTION 32 14 13.16**  
**PAVING SLABS ON A CONCRETE BASE**  
**(1995 MasterFormat Section 02784)**

*Note: This guide specification for the U.S. is for paving slabs on a sand bed over concrete for pedestrian applications. Paving slabs no larger than 300 mm x 300 mm paving slabs are recommended for this type of sand-set application. If larger slabs are specified, cement mixed in the bedding sand is recommended (sometimes called "dry pack"). Slabs installed with these methods are not recommended for areas subject to vehicular traffic. The text must be edited to suit specific project requirements. This Section includes the term "Architect." Edit this term as necessary to identify the design professional in the General Conditions of the Contract.*

**PART 1 GENERAL**

**1.01 SUMMARY**

- A. Section Includes
  - 1. Concrete paving slabs.
  - 2. Bedding and joint sand.
  - 3. Geotextiles.
  - 4. Edge restraints.
  - 5. [Cleaner, Sealers, Joint Sand Stabilizers]
- B. Related Sections
  - 1. Section: [ ]- Curbs and Drains.
  - 2. Section: [ ]- Concrete Base.
  - 3. Section: [ ]- Pavements, Asphalt and Concrete.
  - 4. Section: [ ]- Geotextiles.

*Note: Pavements subject to vehicles should be designed in consultation with a qualified civil engineer, in accordance with established pavement design procedures and in accordance with the ICPI Tech Spec technical bulletins. Use the current year reference.*

**1.02 REFERENCES**

- A. American Society of Testing and Materials (ASTM):
  - 1. C 33, Specification for Concrete Aggregates.
  - 2. C 136, Method for Sieve Analysis for Fine and Coarse Aggregate.
  - 4. C 144, Standard Specification for Aggregate for Masonry Mortar.
- B. Canadian Standards Association (CSA)
  - 1. A231.1, Precast Concrete Paving Slabs.
- C. Interlocking Concrete Pavement Institute (ICPI)
  - 1. ICPI Tech Spec Technical Bulletins

**1.03 SUBMITTALS**

- A. In accordance with Conditions of the Contract and Division 1 Submittal Procedures Section.
- B. Manufacturer's drawings and details: Indicate perimeter conditions, relationship to adjoining materials and assemblies, [expansion and control joints,] concrete paving slab [layout,] [patterns,] [color arrangement,] installation [and setting] details.
- C. Sieve analysis per ASTM C 136 for grading of bedding and joint sand.
- D. Concrete paving slabs:
  - 1. [Four] representative full-size samples of each slab type, thickness, color, finish that indicate the range of color variation and texture expected in the finished installation. Color(s) selected by [Architect] [Engineer] [Landscape Architect] [Owner] from manufacturer's available colors.
  - 2. Accepted samples become the standard of acceptance for the work.
  - 3. Test results from an independent testing laboratory for compliance of paving unit

- requirements to CSA A231.1.
      - 4. Manufacturer's certification of concrete slabs by ICPI as having met applicable CSA standards.
      - 5. Manufacturer's catalog product data, installation instructions, and material safety data sheets for the safe handling of the specified materials and products.
    - E. Paving Slab Installation Subcontractor:
      - 1. A copy of Subcontractor's current certificate from the Interlocking Concrete Pavement Institute Concrete Paver Installer Certification program.
      - 2. Job references from projects of a similar size and complexity. Provide Owner/Client/General Contractor names, postal address, phone, fax, and email address.
- 1.04 QUALITY ASSURANCE
- A. Paving Subcontractor Qualifications:
    - 1. Utilize an installer having successfully completed concrete paving slab installation similar in design, material, and extent indicated on this project.
    - 2. Utilize an installer holding a current certificate from the Interlocking Concrete Pavement Institute Concrete Paver Installer Certification program.
  - B. Regulatory Requirements and Approvals: [Specify applicable licensing, bonding or other requirements of regulatory agencies].
  - C. Mock-Ups:
    - 1. Install a 7 ft x 7 ft (2 x 2 m) slab area.
    - 2. Use this area to determine surcharge of the bedding sand layer, joint sizes, lines, laying pattern(s), color(s), and texture of the job.
    - 3. This area will be used as the standard by which the work will be judged.
    - 4. Subject to acceptance by owner, mock-up may be retained as part of finished work.
    - 6. If mock-up is not retained, remove and properly dispose of mock-up.
- 1.05 DELIVERY, STORAGE & HANDLING
- A. General: Comply with Division 1 Product Requirement Section.
  - B. Comply with manufacturer's ordering instructions and lead-time requirements to avoid construction delays.
  - C. Delivery: Deliver materials in manufacturer's original, unopened, undamaged containers packaging with identification labels intact.
    - 1. Coordinate delivery and paving schedule to minimize interference with normal use of buildings adjacent to paving.
    - 2. Deliver concrete paving slabs to the site in steel banded, plastic banded or plastic wrapped packaging capable of transfer by fork lift or clamp lift.
    - 3. Unload slabs at job site in such a manner that no damage occurs to the product.
  - D. Storage and Protection: Store materials protected such that they are kept free from mud, dirt, and other foreign materials. [Store concrete paving slab cleaners and sealers per manufacturer's instructions.]
    - 1. Cover bedding sand and joint sand with waterproof covering if needed to prevent exposure to rainfall or removal by wind. Secure the covering in place.
- 1.06 PROJECT/SITE CONDITIONS
- A. Environmental Requirements:
    - 1. Do not install sand or slabs during heavy rain or snowfall.
    - 2. Do not install sand and slabs over frozen aggregate base materials.
    - 3. Do not install frozen sand or saturated sand.
    - 4. Do not install slabs on frozen or saturated sand.
- 1.07 MAINTENANCE

- A. Extra Materials: Provide [Specify area] [Specify percentage.] additional material for use by owner for maintenance and repair.
- B. Slabs shall be from the same production run as installed materials.

**PART 2 PRODUCTS**

**2.01 CONCRETE PAVING SLABS**

*Note: Concrete paving slabs may have spacer bars on each unit. They are highly recommended for mechanical installation. Manually installed slabs may be installed with or without spacer bars.*

- A. Manufacturer: [Specify ICPI member manufacturer name.].
  - 1. Contact: [Specify ICPI member manufacturer contact information.].
- B. Concrete Paving Slabs:
  - 1. Slab type: [Specify name of product group, family, series, etc.].
    - a. Material Standard: Comply with material standards in CSA A231.1: 650 psi (4.5 MPa) average flexural strength. Freeze-thaw scaling testing requirements shall be waived for applications not exposed to freezing conditions.
    - b. Color [and finish]: [Specify color.] [Specify finish].
    - d. Size: [Specify.] inches [({Specify.}mm)] x [Specify.] inches [({Specify.}mm)] x [Specify.] inches [({Specify.} mm)] thick.
    - e. Manufactured in a plant where paving products are certified by ICPI as having passed manufacturer designated [ASTM] [CSA] requirements in this specification.

**2.02 PRODUCT SUBSTITUTIONS**

- A. Substitutions: No substitutions permitted.

**2.03 BEDDING AND JOINT SAND**

- A. Provide bedding and joint sand as follows:
  - 1. Clean, non-plastic, free from deleterious or foreign matter, symmetrically shaped, natural or manufactured from crushed rock.
  - 2. Do not use limestone screenings, stone dust, or sand for the bedding sand material that do not conform to the grading requirements of ASTM C 33.
  - 3. Do not use mason sand or sand conforming to ASTM C 144 for the bedding sand.
  - 4. Where concrete paving slabs are subject to vehicular traffic, utilize sands that are as hard as practically available.
  - 5. Sieve according to ASTM C 136.
  - 6. Bedding Sand Material Requirements: Conform to the grading requirements of ASTM C 33 with modifications as shown in Table 1.

Table 1  
ASTM C 33 Grading Requirements for Bedding Sand

Sieve Size	Percent Passing
3/8 in. (9.5 mm)	100
No. 4 (4.75 mm)	95 to 100
No. 8 (2.36 mm)	85 to 100
No. 16 (1.18 mm)	50 to 85
No. 30 (0.600 mm)	25 to 60
No. 50 (0.300 mm)	10 to 30
No. 100 (0.150 mm)	2 to 10

No. 200 (0.075 mm) 0 to 1

*Note: Coarser sand than that specified in Table 2 below may be used for joint sand including C 33 or A23.1 material as shown in Table 1. Use material where the largest sieve size easily enters the smallest joints. For example, if the smallest slab joints are 2 mm wide, use sand 2 mm and smaller in particle size. If C 33 sand is used for joint sand, extra effort may be required in sweeping material and compacting the slabs in order to completely fill the joints.*

7. Joint Sand Material Requirements: Conform to the grading requirements of ASTM C 144 as shown with modifications in Table 2 below:

Sieve Size	Natural Sand	Manufactured Sand
	Percent Passing	Percent Passing
No. 4 (4.75 mm)	100	100
No. 8 (2.36 mm)	95 to 100	95 to 100
No. 16 (1.18 mm)	70 to 100	70 to 100
No. 30 (0.600 mm)	40 to 75	40 to 100
No. 50 (0.300 mm)	10 to 35	20 to 40
No. 100 (0.150 mm)	2 to 15	10 to 25
No. 200 (0.075 mm)	0 to 1	0 to 10

#### 2.04 EDGE RESTRAINTS

*Note: Specify specific components of a system, manufactured unit or type of equipment. See ICPI Tech Spec 3, Edge Restraints for Interlocking Concrete Pavements for guidance on selection and design of edge restraints.*

- A. Provide edge restraints installed around the perimeter of all interlocking concrete paving unit areas as follows:
1. Manufacturer: [Specify manufacturer].
  2. Material: [Plastic] [Concrete] [Aluminum] [Steel] [Pre-cast concrete] [Cut stone] [Concrete].
  3. Material Standard: [Specify material standard].

#### 2.05 ACCESSORIES

- A. Provide accessory materials as follows:
1. Geotextile Fabric:
    - a. Material Type and Description: [Specify material type and description].
    - b. Material Standard: [Specify material standard].
    - c. Manufacturer: [Acceptable to concrete paving slab manufacturer] [Specify manufacturer].

*Note: Delete article below if cleaners, sealers, and/or joint sand stabilizers are not specified.*

2. [Cleaners] [Sealers] [Joint sand stabilizers]
  - a. Material Type and Description: [Specify material type and description].
  - b. Material Standard: [Specify material standard].
  - c. Manufacturer: [Specify manufacturer].

### PART 3 EXECUTION

## 3.01 ACCEPTABLE INSTALLERS

- A. [Specify acceptable paving subcontractors].

*Note: The elevations and surface tolerance of the base determine the final surface elevations of concrete paving slabs. The paving slab installation contractor cannot correct deficiencies in the base surface with additional bedding sand or by other means. Therefore, the surface elevations of the base should be checked and accepted by the General Contractor or designated party, with written certification to the paving subcontractor, prior to placing bedding sand and concrete paving slabs.*

## 3.02 EXAMINATION

- A. Acceptance of Site Verification of Conditions:
1. General Contractor shall inspect, accept and certify in writing to the paving slab installation subcontractor that site conditions meet specifications for the following items prior to installation of interlocking concrete paving slabs.
    - a. Verify that subgrade preparation, compacted density and elevations conform to specified requirements.
    - b. Verify that geotextiles, if applicable, have been placed according to drawings and specifications.
    - c. Verify that [Aggregate] [Cement-treated] [Asphalt-treated] [Concrete] [Asphalt] base materials, thickness, [compacted density], surface tolerances and elevations conform to specified requirements.
    - d. Provide written density test results for soil subgrade, [aggregate] [cement-treated][asphalt-treated][asphalt] base materials to the Owner, General Contractor and paving slab installation subcontractor.
    - e. Verify location, type, and elevations of edge restraints, [concrete collars around] utility structures, and drainage holes and inlets.
  2. Do not proceed with installation of bedding sand and concrete paving slabs until [subgrade soil and] base conditions are corrected by the General Contractor or designated subcontractor.

## 3.03 PREPARATION

- A. Verify that concrete base is clean and dry, certified by General Contractor as meeting material, installation and grade specifications.
- B. Verify that base [and geotextile] is ready to support sand, [edge restraints,] and, slabs and imposed loads.
- C. Edge Restraint Preparation:
1. Install edge restraints per the drawings [and manufacturer's recommendations] [at the indicated elevations].

*Note: Retain the following two subparagraphs if specifying edge restraints that are fastened to the base.*

2. Mount directly to concrete base. Do not install on bedding sand.

## 3.04 INSTALLATION

- A. Spread bedding sand evenly over the base course and screed to a nominal 1 in. (25 mm) thickness. Spread bedding sand evenly over the base course and screed rails, using the rails and/or edge restraints to produce a nominal 1 in. (25 mm) thickness, allowing for specified variation in the base surface.
1. Compact screeded bedding sand with at least two passes of vibratory plate compactor having a centrifugal compaction force of 4,000 lbs. (18 kN) and a frequency of 75 to 90 Hz.
  2. Loosen 3 to 4 mm of the bedding sand surface with a rake. Maintain a consistent thickness of loosened bedding sand with no clumps or areas with little or no

- loosened sand on the surface.
- 3. Do not disturb sand.
- 4. Screeded area shall not substantially exceed that which is covered by slabs in one day.
- 5. Do not use bedding sand to fill depressions in the base surface.

*Note: When initially placed on the bedding sand, manually installed slabs often touch each other, or their spacer bars if present. Joint widths and lines (bond lines) are straightened and aligned to specifications with rubber hammers and pry bars as paving proceeds.*

- B. Lay paving slabs in pattern(s) shown on drawings. Place units hand tight without using hammers. Make horizontal adjustments to placement of laid slabs with rubber hammers as required.

*Note: Contact manufacturer of concrete paving slabs for recommended joint widths.*

- C. Provide joints between slabs [1/16 in. and 3/16 in. (2 and 5 mm)] wide. No more than 5% of the joints shall exceed [1/4 in. (6 mm)] wide to achieve straight bond lines.
- D. Joint (bond) lines shall not deviate more than  $\pm 1/2$  in. ( $\pm 15$  mm) over 50 ft. (15 m) from string lines.
- E. Fill gaps at the edges of the paved area with cut slabs or edge units.
- F. Cut slabs to be placed along the edge with a [double blade slab splitter or] masonry saw. Cut units shall be no smaller than [1/3 of a whole slab].

*Note. Specify requirements for edge treatment in paragraph below.*

- G. [Adjust bond pattern at pavement edges such that cutting of edge slabs is minimized.]  
[Cut slabs at edges as indicated on the drawings.]
- H. Keep skid steer and forklift equipment off newly laid slabs that have not received initial compaction and joint sand.
- I. After an area is completely paved, compact the units into the sand with a mechanical plate vibrator using rollers or a neoprene pad.
- J. Use a low-amplitude plate compactor capable of at least minimum of 4,000 lbf (18 kN) at a frequency of 75 to 100 Hz. Remove any cracked or damaged slabs and replace with new units.
- K. Simultaneously spread, sweep and compact dry joint sand into joints continuously until full. This will require at least 4 to 6 passes with a plate compactor. Do not compact within 6 ft (2 m) of unrestrained edges of paving units.
- K. All work within 6 ft. (2 m) of the laying face must shall be left fully compacted with sand-filled joints at the end of each day or compacted upon acceptance of the work. Cover the laying face or any incomplete areas with plastic sheets overnight if not closed with cut and compacted slabs with joint sand to prevent exposed bedding sand from becoming saturated from rainfall.
- L. Remove excess sand from surface when installation is complete.

*Note: Excess joint sand can remain on surface of paving slabs to aid in protecting their surface especially when additional construction occurs after their installation. If this is the case, delete the article above and use the article below. Designate person responsible for directing timing of removal of excess joint sand.*

- M. Allow excess joint sand to remain on surface to protect slabs from damage from other trades. Remove excess sand when directed by [Architect].
- N. Surface shall be broom clean after removal of excess joint sand.

3.05 FIELD QUALITY CONTROL

*Note: Surface tolerances on flat slopes should be measured with a rigid straightedge. Tolerances on complex contoured slopes should be measured with a flexible straightedge capable of conforming to the complex curves on the pavement surface.*

- A. The final surface tolerance from grade elevations shall not deviate more than  $\pm 3/8$  in. ( $\pm 10$  mm) under a 10 ft (3 m) straightedge.
- B. Check final surface elevations for conformance to drawings.
- C. The surface elevation of slabs shall be 1/8 in. to 1/4 in. (3 to 6 mm) above adjacent drainage inlets, concrete collars or channels.
- D. Lippage: No greater than 1/8 in. (3 mm) difference in height between adjacent slabs.

*Note: Cleaning and sealing may be required for some applications. See ICPI Tech Spec 5, Cleaning and Sealing Interlocking Concrete Pavements for guidance on when to clean and seal the slab surfaces, and when to stabilize joint sand. Delete article below if cleaners, sealers, and or joint sand stabilizers are not applied.*

3.06 [CLEANING] [SEALING] [JOINT SAND STABILIZATION]

- A. [Clean] [Seal] [Apply joint sand stabilization materials between] concrete paving slabs in accordance with the manufacturer's written recommendations.

3.07 PROTECTION

- A. After work in this section is complete, the General Contractor shall be responsible for protecting work from damage due to subsequent construction activity on the site.

END OF SECTION